



Silicone Sealant

Products - Cat 1 - Putty and Caulks



DESCRIPTION

Black Swan Silicone Sealant is a paste-like, one component material that cures to a tough, rubbery solid upon exposure to moisture in the air. Because it does not flow due to its own weight, this sealant can be applied overhead or on sidewall joints and surfaces without sagging, slumping or running off. It adheres to clean metal, glass, most types of wood, silicone resin, vulcanized silicone rubber, ceramic, natural and synthetic fiber, painted surfaces and many plastics.

Silicone Sealant is resistant to moisture, aging, shrinkage, cracking, and discoloring. It does not contain a solvent. Packaged in squeeze tubes and cartridges in colors of white and clear.

USES

1. Caulking and sealing around bathtubs, shower stalls, bathroom vanities and kitchen counters and sinks.
2. Sealing around exterior windows and doors to draft and waterproof.
3. Replacing ceramic tiles and making new gaskets for dishwasher doors, skid and mark proofing vases, ashtrays and picture frames.
4. Repairing or installing body side molding; repairing or making gaskets for automotive and boat windows and doors and installing through hull fittings in boats above the waterline.
5. For making gaskets to replace costly paper gaskets for timing chain valve covers and for water pump or thermostat housings... any application that requires a permanently flexible waterproof seal that will withstand moisture, heat and vibration.

LIMITATIONS

1. **Silicone Sealant** is not recommended for porous substrates such as concrete, stone or marble.
2. Do not use **Silicone Sealant** on bituminous substrates, substrates based on natural rubber, chloroprene or EPDM or on building materials which might bleed oils, plasticizer or solvents.
3. Because acetic acid is released during curing, it can corrode mirror silver and sensitive metals such as copper, brass and lead. **SILICONE SEALANT** is not suitable for food contact application.
4. This product is neither tested nor represented as suitable for food, medical or pharmaceutical uses.

TECHNICAL DATA

Cure System	Acetoxy
Application Temperature (° C)	+5 TO +40
Specific Gravity (G/ML)	1.02
Extrusion Rate (G/MIN)	510
Skin-Over Time (23C, 50% R.H.)	11 MINUTES
Tack-Free Time (23C, 50% R.H.)	20 MINUTES
Cure Rate (23C, 50% R.H.)	
1 Day	1.5 MM
3 Day	4.0 MM

The following results were obtained from a 2 mm thick film of fully cured silicone sealant:

E-MODULUS 100%	0.56 MPa
TENSILE STRENGTH	190 MPa
ELONGATION AT BREAK	500%
HARDNESS (SHORE A)	24

DIRECTIONS

1. Surfaces must be clean, dry and free from grease, dust and frost. Non-porous surfaces: aluminum, glass, etc., should be cleaned with a suitable solvent for the substrate. Adhesion to plastic and metal surfaces can be improved by using a primer.
2. Cut nozzle or tip.
3. Apply to surface pushing sealant ahead of nozzle or tip. Assure contact with both sides of joint.

4. Complete any additional tooling and remove excess sealant with wet stick or knife immediately. Clean excess caulk off surface immediately with clean rag.

5. Sealant cures dry to touch in 30 minutes and fully cures in 24 hours. Remove excess sealant with a razor blade (single edge) or knife.

CAUTION

Warning! Direct contact of uncured sealant can irritate eyes and may irritate skin. Overexposure to vapor may irritate eyes, nose and throat.

UPC NUMBER AND CARTON INFORMATION

STOCK NO.	SIZE /COLOR	UPC NUMBER	CARTON CUBIC FEET
01095	3 oz. / WHITE	0 54647 01095 3	.253
01100	3 oz. / CLEAR	0 54647 01100 4	.253
01105	10.3 oz. / WHITE	0 54647 01105 9	.542
01110	10.3 oz. / CLEAR	0 54647 01110 3	.542
MSDS - Silicone Sealant - White			
MSDS - Silicone Sealant - Clear			
Buy Now			